

ECSE-2210 Microelectronics Technology
Homework 2 – Solution

1. Always, $np \approx n_i^2$

$$\text{At 300 K, } n = 10^{17} \text{ cm}^{-3}, \quad n_i = 10^{10} \text{ cm}^{-3}, \quad p = 10^3 \text{ cm}^{-3}$$

$$\text{At 200 K, } n = 10^{17} \text{ cm}^{-3}, \quad n_i = 10^5 \text{ cm}^{-3}, \quad p = 10^{-7} \text{ cm}^{-3}$$

That is, the hole concentration at 200 K is extremely small. You will find only one hole in a volume of 10^7 cm^3 of Si !

2. a) At room temperature in Si, $n_i = 10^{10} \text{ cm}^{-3}$. Thus here $N_D \gg N_A, N_D \gg n_i$ and

$$n = N_D = 10^{15} \text{ cm}^{-3}$$

$$p = n_i^2 / N_D = 10^5 \text{ cm}^{-3}$$

b) Since $N_D \ll N_A, N_A \gg n_i$

$$p = N_A = 10^{16} \text{ cm}^{-3}$$

$$n = n_i^2 / N_A = 10^4 \text{ cm}^{-3}$$

c) Here we must retain both N_D and N_A , but $N_D - N_A \gg n_i$

$$n = N_D - N_A = 10^{15} \text{ cm}^{-3}$$

$$p = n_i^2 / (N_D - N_A) = 10^5 \text{ cm}^{-3}$$

d) We deduce from Figure 2.20 that, at 450 K, n_i (Si) $\approx 5 \times 10^{13} \text{ cm}^{-3}$. Clearly, n_i is comparable to N_D and we must use Eq. 2.29a

$$n = N_D/2 + [(N_D/2) + n_i^2]^{1/2} = 1.21 \times 10^{14} \text{ cm}^{-3}$$

$$p = n_i^2 / n = 2.07 \times 10^{13} \text{ cm}^{-3}$$

e) We conclude from figure 2.20, that at 650 K, $n_i = 10^{16} \text{ cm}^{-3}$ Here $n_i \gg N_D$

$$p = n_i = 10^{16} \text{ cm}^{-3}$$

$$n = n_i = 10^{16} \text{ cm}^{-3}$$

3)

(i) As established in the text [Eq.(2.36)],

$$E_i = \frac{E_c + E_v}{2} + \frac{3}{4} kT \ln(m_p^*/m_n^*)$$

Taking m_p^*/m_n^* to be temperature independent and employing the values listed in Table 2.1, one concludes

part	T(K)	kT (eV)	E_i displacement from midgap (eV)
(a-c)	300	0.0259	-0.0073
(d)	450	0.0388	-0.0109
(e)	650	0.0560	-0.0158

Alternatively, the m_p^*/m_0 and m_n^*/m_0 versus T fit-relationships cited in Exercise 2.4 may be used to compute the m_p^*/m_n^* ratio. One finds

part	T(K)	m_p^*/m_n^*	kT (eV)	E_i displacement from midgap (eV)
(a-c)	300	0.680	0.0259	-0.0075
(d)	450	0.703	0.0388	-0.0103
(e)	650	0.719	0.0560	-0.0139

(ii) $E_F - E_i$ is computed using the appropriate version of Eq.(2.37) or (2.38).

(a) $E_F - E_i = kT \ln(N_D/n_i) = 0.0259 \ln(10^{15}/10^{10}) = 0.298 \text{ eV}$

(b) $E_i - E_F = kT \ln(N_A/n_i) = 0.0259 \ln(10^{16}/10^{10}) = 0.358 \text{ eV}$

(c) $E_F - E_i = kT \ln[(N_D - N_A)/n_i] = 0.0259 \ln(10^{15}/10^{10}) = 0.298 \text{ eV}$

(d) $E_F - E_i = kT \ln(n/n_i) = 0.0388 \ln(1.21 \times 10^{14}/5 \times 10^{13}) = 0.034 \text{ eV}$

(e) $E_F - E_i = kT \ln(n/n_i) \cong 0 \quad \dots (n \cong n_i)$

